

GASOILA[®] E-Seal

GASOILA
CHEMICALS

TECHNICAL DATA

2013

Description

A dark green, opaque, viscous, non-hardening, textured paste with PTFE.

Type

Slow-drying, soft-setting, non-toxic, brushable, without grit. Cures by solvent evaporation providing a durable, long-lasting seal that can be easily disassembled.

Typical Uses

Especially designed for ethanol blended gasoline including E10, E20 & E85.

Substrates

Can be used on brass, copper, stainless steel, aluminum, black pipe, tin, galvanized pipe, ABS plastic, CPVC, nylon, PVC, polyethylene, polypropylene and more.

Chemical Resistance

Excellent resistance to ethanol blended gasoline, kerosene, petroleum solvents, diesel fuel, propane, butane, LPG, water, cutting oils. NOT oxygen.

Set Time

None. For immediate service
Dries to the touch 48-72 hour

Packaging

Available in 1/4 pint, 1/2 pint and pint cans with brush-top lids.

For Chemical Emergency, Spill, Leak,
Fire, Exposure or Accident Call:
CHEMTREC - Day or Night. 1-800-424-9300
KEEP OUT OF THE REACH OF CHILDREN

Product Data Sheet

Safety

Contains no lead, is non-toxic, not a skin sensitizer, and is non-corrosive.

Shelf Life: One year in original containers, when stored at room temperature at or below 80°F (27°C)

Wt./Gal.: 11.35 lbs

Color: Medium/Green

Clean Up: Hand cleaner or alcohol.

Temperature Range

-100°F to 600°F (-73°C to 316°C)
Allow to dry thoroughly before exposing to high temperatures. Remains usable in sub-zero weather.

Pressure Range

Up to 10,000 psi when sealing liquids and up to 3,000 psi with gases. Allow to dry, if possible, before subjecting to pressure.

The information presented is in good faith, but no warranty is given, nor are results guaranteed. Federal Process has no control over physical conditions surrounding application conditions. Federal Process disclaims any liability for untoward results.



FEDERAL PROCESS
CORPORATION



CLEVELAND, OHIO | 216.464.6440 • 800.846.7325

www.gasoila.com

MSDS Sheets Available Online

#DS-ES